SEP 2 4 2007

## Amendments to the Claims:

6508542384

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

A container which can be sealed around at least 4 kg of bananas 1. (Withdrawn) and which, when sealed around the bananas, has an O<sub>2</sub> permeability at 13 °C, per kg of bananas in the container (OP13/kg), of at least 700 ml/atm.24 hrs, an R ratio at 13 °C of at least 3, and an ethylene permeability at 13 °C, per kg of bananas in the container (EtOP13/kg) which is at least 3 times the OP13/kg of the container.

## 2- 10. (Canceled)

- A package which is at a temperature of 13-18°C and 11. (Currently amended) which comprises
  - a sealed container, and (a)
  - within the sealed container, at least 4 kg of bananas which have not yet (b) commenced their climacteric, and a packaging atmosphere around the bananas;

the sealed container having an O<sub>2</sub> permeability at 13 °C, per kg of bananas in the container (OP13/kg), of at least 1500 ml/atm.24 hrs, an R ratio at 13 °C of at least 3. and an ethylene permeability at 13 °C, per kg of bananas in the container (EtOP13/kg) which is at least 3 times the OP13/kg of the container; and the packaging atmosphere being an equilibrium atmosphere in which the oxygen content has a substantially constant value which is from 14 to 19%, the carbon dioxide content has a substantially constant value which is less than 10%, and the total quantity of oxygen and carbon dioxide has a substantially constant value which is less than 20%.

being substantially constant; and

- (ii) containing 14 to 19% of O<sub>2</sub>, and less than 10% of CO<sub>2</sub>, with the total quantity of O<sub>2</sub> and CO<sub>2</sub> being less than 17%.
- 12. (Original) A package according to claim 11 wherein the container includes at least one permeable control member which provides a pathway for O<sub>2</sub>, CO<sub>2</sub> and ethylene to enter or leave the packaging atmosphere and which comprises a gas permeable membrane comprising
  - (a) a microporous polymeric film, and
  - (b) a polymeric coating on the microporous film.
- 13. (Original) A package according to claim 12 wherein the gas-permeable membrane
  - (i) has a P<sub>10</sub> ratio, over at least one 10°C range between -5 and 25 °C of at least 1.5, and
  - (ii) has an oxygen permeability (OTR), at all temperatures between 13 and 25°C, of at least 2,480,000 ml/m².atm.24 hrs (160,000 cc/100 inch².atm.24 hrs).
- 14. (Previously presented) A package according to Claim 13 wherein the microporous polymeric film comprises a network of interconnected pores having an average pore size of less than 0.24 micron, with at least 70% of the pores having a pore size of less than 0.24 micron.
- 15. (Original) A package according to Claim 14 wherein
  - (1) the pores in the microporous film constitute 35 to 80% by volume of the microporous film; and
  - (2) the microporous film comprises
    - (a) a polymeric matrix comprising (i) an essentially linear ultrahigh molecular weight polyethylene having an intrinsic viscosity of at least 18 deciliters/g, or (ii) an essentially linear ultrahigh molecular weight polypropylene having an intrinsic viscosity of at least 6 deciliters/g, or (iii) a mixture of (i) and (ii); and

(a) 30 to 90% by weight, based on the weight of the film, of a finely divided particulate substantially insoluble filler which is distributed throughout the film.

16-20. (canceled)

- 21. (Currently amended) A package which is at a temperature of 13-18°C and which comprises
  - (a) a sealed container which comprises
    - (i) a polyethylene bag, and
    - (ii) at least one permeable control member which provides a pathway for  $O_2$ ,  $CO_2$  and ethylene to enter or leave the packaging atmosphere and which comprises a gas-permeable membrane comprising a microporous polymeric film, and a polymeric coating on the microporous film; and
  - (b) within the sealed container, at least 4 kg of bananas which have not yet commenced their climacteric, and a packaging atmosphere around the bananas; and

the sealed container having an O<sub>2</sub> permeability at 13 °C, per kg of bananas in the container (OP13/kg), of at least 1500 ml/atm.24 hrs, an R ratio at 13 °C of at least 3, and an ethylene permeability at 13 °C, per kg of bananas in the container (EtOP13/kg) which is at least 3 times the OP13/kg of the container; and the packaging atmosphere

- (i) being substantially constant; being an equilibrium atmosphere in which the oxygen content has a substantially constant value which is from 14 to 19%, the carbon dioxide content has a substantially constant value which is less than 10%, and the total quantity of oxygen and carbon dioxide has a substantially constant value which is less than 20%, and
- (ii) being free of ethylene which has been added to the packaging atmosphere from a source of ethylene other than the bananas themselves... and (iii) containing 14 to 19% of O<sub>2</sub>, and less than 10% of CO<sub>2</sub>, with the total quantity of O<sub>2</sub> and CO<sub>2</sub> being less than 17-%.

- 22. (Previously presented)) A package according to claim 21 wherein the gaspermeable membrane
  - (i) has a P<sub>10</sub> ratio, over at least one 10°C range between -5 and 25 °C of at least 1.5, and
  - (ii) has an oxygen permeability (OTR), at all temperatures between 13 and 25°C, of at least 2,480,000 ml/m².atm.24 hrs (160,000 cc/100 inch².atm.24 hrs).
- 23. (Previously presented) A package according to Claim 22 wherein the microporous polymeric film comprises a network of interconnected pores having an average pore size of less than 0.24 micron, with at least 70% of the pores having a pore size of less than 0.24 micron.
- 24. (Previously presented) A package according to Claim 23 wherein
  - (1) the pores in the microporous film constitute 35 to 80% by volume of the microporous film; and
  - (2) the microporous film comprises
    - (a) a polymeric matrix comprising (i) an essentially linear ultrahigh molecular weight polyethylene having an intrinsic viscosity of at least 18 deciliters/g, or (ii) an essentially linear ultrahigh molecular weight polypropylene having an intrinsic viscosity of at least 6 deciliters/g, or (iii) a mixture of (i) and (ii); and
    - (b) 30 to 90% by weight, based on the weight of the film, of a finely divided particulate substantially insoluble filler which is distributed throughout the film.
- 25. (Previously presented) A package according to claim 21 wherein the sealed container contains only the bananas.